

# Styropor® expandable polystyrene

## BF 295M Product



The Chemical Company

### Products and their uses

Styropor BF 295M high pentane product can be used in a wide variety of applications including blocks for panels, general insulation, below grade use, fabrication and flotation with high density and low densities requiring excellent fusion with or without regrind.

### Description

Modified expandable polystyrene (EPS) containing approximately 5.7 – 6.4 wt% pentane as the blowing agent. The BF 295M is supplied as spherical beads with a bulk density of approximately 40 lbs/ft<sup>3</sup> (640 kg/m<sup>3</sup>).

### Packaging and storage

Styropor BF 295M products are packaged in Flexible Intermediate Bulk Containers of 1,763 lbs. (800 kgs). Plastic liners are used to maintain product shelf life by retaining the blowing agent. Styropor products should be stored indoors in a cool place (maximum temperature 80°F). In the unopened bulk containers, the typical shelf life after receipt is 30-60 days. The containers should be protected from rain, snow, frost, direct sunlight and mechanical damage.

Product Specifications			
Material Type	Bead Size (mm)	Applications	Pre-puff Age (dependent on density)
Type I, VIII, II, IX	0.85 – 1.70	Foam panel insulation, Geofam, SIPS, EIFS, ETICS and Flooring	10 to 72 hours

### Typical expanded density range\*

0.90 – 3.0 lbs/ft<sup>3</sup> (14.1 – 48.1 g/L)

\*(All recommended densities are first pass through batch expanders.)

### Processing

Polystyrene foams made from Styropor BF 295M products are produced in three stages: Pre-expansion, intermediate aging and molding. Full details are given in the brochure *Processing Styropor*.

### Pre-expansion

The minimum achievable density is partly dependent on the pre-expansion equipment and technique used. For example, a state-of-the-art batch expander is capable to pre-expand 10 to 15% lower versus a continuous expander. Care should be taken during expansion as prolonged steam times will result in excessive loss of pentane, damage to the pre-puff and ultimate difficulty in achieving acceptable bead fusion during molding.

### Intermediate aging

The minimum recommended pre-puff aging period for this product (dependent on density) is ten (10) to seventy-two (72) hours. Age at which the product is ready to mold is dependent on ambient temperature, environmental conditions, design of storage silos and molding equipment. For low to low-mid density block molding applications, a minimum age period of ten (10) to twenty (20) hours prior to molding can be attempted. At mid to high densities, a minimum age period of twenty-four (24) to seventy-two (72) hours is recommended. Consideration of bead capabilities should be taken when aging products in excess of forty-eight (48) hours.

### Molding

This product is intended for molding on automatic molding machines. Molding can be accomplished under a wide range of conditions and densities.

### **Regulatory Compliance**

EPS foams manufactured from Styropor BF 295M comply with surface burning characteristics (ASTM E-84), (CAN/ULC S102.2) UL, ULC Building Products classification BRYX, BRYX2 & BTLIC under listing R-5917. In addition to NFPA 286-11 *Methods of Fire Test for Evaluating contribution of Wall and Ceiling Interior Finish to Room fire Growth*. (ASTM C-578), (CAN/ULC S701-11) requirements of U.S. and Canada model building codes. ICC Evaluation Service report ER 1498 contains specific code compliance criteria for Styropor BF 295M. EPS foams manufactured from Styropor BF 295M product meets Packaging UL 94, QMFZ, QMFZ2 classification requirements and have obtained a HF1 rating as described in UL listing E-54675.

### **Safety**

Styropor products and the finished foam products should not be exposed to ignition sources (including open flame, sparks, or electrostatic discharges) during storage, processing, shipment and application. Adequate ventilation in all processing areas must be provided to prevent hazardous accumulations of hydrocarbon vapors. For complete safety precautions and recommendations, refer to the Styropor bulletin S-6 *Fire Safety Precautions in Styropor Processing Plants* and appropriate Material Safety Data Sheets.

### **Useful links:**

#### **ICC-ES**

[http://www.icc-es.org/reports/pdf\\_files/ICC-ES/ESR-1498.pdf](http://www.icc-es.org/reports/pdf_files/ICC-ES/ESR-1498.pdf)

#### **Intertek**

[http://whdirectory.intertek.com/Pages/DLP\\_Search.aspx](http://whdirectory.intertek.com/Pages/DLP_Search.aspx)

#### **UL**

<http://database.ul.com/cgi-bin/XYV/cgifind.new/LISEXT/1FRAME/srch.res.html>

**Important:** While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCT DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data, and information given or results obtained, all such being given and accepted at your risk.

*Values shown are based on limited testing and are not intended to be used in establishing maximum or minimum ranges for specification purposes.*

STYROPOR is a registered trademark of BASF AG.  
Copyright © 2012- BASF Corporation

BASF Corporation  
1609 Biddle Avenue  
Wyandotte, MI 48192  
973-907-6377

<http://www.basf.com>



The Chemical Company