

Styropor® expandable polystyrene BFL F-95 Product Series



Products and their uses

Styropor BFL products include BFL 295, BFL 395, BFL 397, BFL 397S and BFL 495. Styropor BFL F-95 products can be used in a wide variety of applications including blocks for panels, general insulation, below grade use, fabrication, flotation, and general packaging. Additional applications include insulated concrete forms, thin or thick walled custom molding, and other general protective packaging. The intended uses of each product grade are outlined in Table 1.

Description

Expandable polystyrene (EPS) containing approximately 3.45 – 3.65 wt% pentane as the blowing agent.

All products are supplied as spherical beads with a bulk density of approximately 40 lbs·ft⁻³ (640 kg·m⁻³). The bead size range for each product is shown in Table 2.

Styropor BFL F-95 products are compatible with many anti-stat, mineral oil and color additives that can be added during processing.

Application Compliance

EPS foams manufactured from Styropor BFL F-95 comply with surface burning characteristics (ASTM E-84) and physical property (ASTM C- 578) requirements of U.S. model building codes. National Evaluation Service report NER-479 and ICC Evaluation Service report ESR-1498 contain specific code compliance criteria for Styropor BFL. EPS foams manufactured from Styropor BFL meet UL 94 classification requirements and have obtained an HF-1 rating as described in UL listing E54675. Technical specifications for the BFL F-95 products are listed in Table 2.

Packaging and storage

Styropor BFL F-95 products are packaged in Flexible Intermediate Bulk Containers of 1,763 lbs (800 kgs). Plastic liners are used to maintain product shelf life by retaining the blowing agent.

Styropor products should be stored in a cool place. In the unopened bulk containers, the typical shelf life after receipt is 30-60 days. The containers should be protected from rain, snow, frost, direct sunlight and mechanical damage.

Table 1

Product	Intended uses
Styropor BFL 295	Block molding applications, low and high densities requiring excellent fusion or with regrind
Styropor BFL 395	Block molding applications, especially suited for excellent surface cut appearance
Styropor BFL 397	Shape molding applications requiring modified material or high density block molding applications with excellent surface cut appearance
Styropor BFL 397S	Fast cycle, short age shape molding, thick parts and ICF applications requiring modified material or high density block molding applications with excellent surface appearance
Styropor BFL 495	Shape molding for thin walled applications with fast cycles and excellent surface finish requiring modified material

Table 2: Technical product specifications

Product	Pentane content	Moisture content	Bead size (mm)	
Styropor BFL 295	3.45–3.65 %	1.2% max	0.85 – 1.70	≥97%
Styropor BFL 395	3.45-3.65%	1.2% max	0.85 – 1.25	≥97%
Styropor BFL 397	3.45-3.65%	1.2% max	0.60 – 1.25	≥97%
Styropor BFL 397S	3.45-3.65%	1.2% max	0.60 – 1.25	≥97%
Styropor BFL 495	3.45-3.65%	1.2% max	0.42 – 0.85 2% max < 0.425	≥97%

Processing

Polystyrene foams made from Styropor BFL F-95 products are produced in three stages: pre-expansion, intermediate aging and molding. Full details are given in the brochure *Processing Styropor*.

Pre-expansion

The minimum density achievable depends on the pre-expansion equipment and technique used. In properly functioning batch pre-expanders, the products can be processed to the bulk densities shown in Table 3. In continuous pre-expanders, they can be processed to bulk densities of 1.6 – 1.8 lbs·ft⁻³ (25 – 30 kg·m⁻³). Care should be taken during expansion, as prolonged steam times will result in excessive loss of pentane and difficulty in achieving acceptable fusion during molding.

Table 3

Product	Typical expanded density range
Styropor BFL 295	0.90-7.0 lb/ft ⁻³ (14-110 kg·m ⁻³)
Styropor BFL 395	0.90-7.0 lbs/ft ⁻³ (14-110 kg·m ⁻³)
Styropor BFL 397S	1.1-5.0 lbs/ft ⁻³ (18-80 kg·m ⁻³)
Styropor BFL 397	1.1-5.0 lbs/ft ⁻³ (18-80 kg·m ⁻³)
Styropor BFL 495	1.1-4.0 lbs/ft ⁻³ (18-65 kg·m ⁻³)

Intermediate aging

For information please refer to the specific S-2 data sheet.

Molding

These products are intended for molding on automatic molding machines. Molding can be accomplished under a wide range of conditions and densities.

Safety

Styropor products and the finished foam products should not be exposed to ignition sources (including open flame, sparks, or electrostatic charges) during storage, processing, shipment and application. Adequate ventilation in all processing areas must be provided to prevent hazardous accumulations of hydrocarbon vapors.

For complete safety precautions and recommendations, refer to the Styropor bulletin S-6 *Fire Safety Precautions in Styropor Processing Plants* and appropriate Material Safety Data Sheets.

OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data, and information given or results obtained, all such being given and accepted at your risk.

Values shown are based on limited testing and are not intended to be used in establishing maximum or minimum ranges for specification purposes.

IMPORTANT: While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCT DESCRIBED OR DESIGNS, DATA OR MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART**

BASF Corporation
Plastic Foams
1609 Biddle Avenue
Wyandotte, MI 48192
973-907-6377

<http://www.plasticsportal.com>

STYROPOR is a registered trademark of BASF AG

Copyright © 2005 BASF Corporation

